

Balmerol[®] SC HT Grease

Superior Performance Calcium Sulphonate Complex Grease

Technical Data Sheet

Product Description:

Balmerol SC HT Grease is premium grade high temperature extreme pressure grease which combines the unique features of over base calcium sulphonate complex thickener with high VI solvent refine mineral oil. The complex thickener provides excellent thermal stability, extreme pressure & anti-wear properties at high temperatures and maintains excellent viscosity-temperature reversibility under severe working conditions, which are unmatched by other soap/non-soap base grease.

Features & Benefits:

Balmerol SC HT grease provides the following benefits:

- Very wide operating temperature range (-) 6°C to (+) 180°C
- Resistance to intermittently temperature shoot-up for short duration
- Provides superior protection against corrosion and wear with extension of equipment life
- Resistance to water wash out
- Extended re-lubrication intervals
- Reduce Energy consumption (low co-efficient of friction)
- Lead and Chlorine free

Applications / Recommendations:

- Balmerol SC HT grease is specially recommended for all heavy duty steel plants & engineering applications where resistance to high temperatures, loads, humidity and water is critical
- Typical applications of Balmerol SC HT Grease include continuous casters, couplings & run-out rolls bearing in steel plants, wheel bearings and CV joints in automobiles, rock crushers and conveyors in mining and bearings & spindles in pulp and paper mills

Balmerol® SC HT Grease

Superior Performance Calcium Sulphonate Complex Grease

Technical Data Sheet

Typical Properties:

Balmerol SC HT Grease	
Properties	SC HT Grease
Colour	Light Brown
Appearance	Smooth, Tacky
Thickener type	Calcium Sulphonate Complex
Base Oil Type	Mineral
Base Oil Viscosity, cst @ 40°C, min, ASTM D 445	230
NLGI Grade	2/1
Worked Penetration 60/60 strokes at 25°C, ASTM D 217	280 - 310
Penetration Change after 100000 strokes, max., ASTM D 217 (Units)	± 10%
Dropping Point °C, min, ASTM D 2265	320+
Water wash out @ 80°C, % loss, max. ASTM D 1264	1.0
Emcor Rust test rating, IP -220	0,0
Four Ball Wear test, Scar Dia-in mm @ 1450 rpm, 70°C, 1 hr,max, ASTM D 2266	0.60
Four Ball Weld load, kgs, min., ASTM D 2596	400
Timken OK Load, lbs, ASTM D 2509	55
Pressure Oil separation test, ASTM D 1742	Nil
Oxidation stability test: Drop in pressure after 100 hrs, 3.0 psi, max	3

Health and Safety:

Balmerol SC HT Grease is not expected to produce adverse effects on health when used for the intended application and the recommendations provided in the Material Safety Data Sheet (MSDS) are followed. For MSDS please contact your local Balmer Lawrie Marketing / Technical Service team.

For Further Information, contact:

Balmer Lawrie & Co. Ltd.
SBU: Greases & Lubricants (G&L) Division
P- 43, Hide Road Extension
Kolkata: 700088
www.balmerlawrie.com